

After establishing such an ideal system, it is then possible to 'dope' the system by introducing impurities into it, thereby allowing control over its electronic transport properties according to one's specific needs."

DNA Used as a Template for Nanolithography

DNA is one of the most popular building blocks of nanotechnology and is commonly used to construct ordered nanoscale structures with controlled architectures. For the most part, DNA is looked upon as a promising building block for fabricating microelectronic circuits from the bottom up. Now, A. Woolley and H. Becerril of Brigham Young University are proposing the marriage of DNA self-assembly with standard microfabrication and lithography tools to form features such as nanochannels, nanowires, and nanoscale trenches. This discovery, reported in the September 3 issue of *Small* (p. 1534; DOI: 10.1002/smll.

200700240) could open new avenues for nanofabrication at dimensions not accessible by conventional optical lithography.

The researchers have developed a method to use DNA molecules as templates to define patterns on substrates. They deposited metal films over DNA molecules aligned on a substrate. The DNA molecules essentially act as nanostencils to define sub-10-nm-sized patterns on the substrate. The researchers call this process "DNA shadow nanolithography" because the metal film is deposited at an angle and the shadow cast by the DNA molecules defines the dimensions of the features on the substrate.

Anisotropic etching of the patterned surfaces using reactive gas plasmas, a commonly used fabrication tool in the semiconductor industry, yields high-aspect-ratio trenches on the substrate. The trenches can be sealed at the top to form continuous enclosed nanochannels.

Alternatively, the trenches can be chemically functionalized and used as templates for the deposition of metal nanowires such as those of nickel, copper, or silver. The templated trenches and nanowires have lateral dimensions of less than 30 nm and can be tailored to be less than 10 nm. The exact dimensions of the trenches can be varied by tuning the angle of deposition and the thickness of the deposited film.

The researchers said that it should be possible to transfer complex patterns onto substrates using surface-aligned DNA molecules. "One remarkable aspect of this technology is that it utilizes the patterning ability of DNA without requiring the nucleic acid to remain in the final construct," said Woolley, adding that the nanostructures fabricated by DNA shadow nanolithography could find use as nanofluidic channels and chemical sensors. □



Dates to Remember

September 1, 2007	Competition Start Date
December 15, 2007	Team Registration Deadline
January 22, 2008	Entry Postmark Deadline

www.mrs.org/entrepreneur

JANIS

CRYOSTATS FOR MÖSSBAUER SPECTROSCOPY



- Closed cycle (10 K and 4 K) or helium-cooled systems available
- Sample in helium gas for fast sample exchange
- Ideal for cooling powder or foil samples with poor thermal conductivity
- Closed cycle system includes vibration isolation stand for ultra-low line broadening: 0.01 mm/s

Janis Research Company
 2 Jewel Drive Wilmington, MA 01887 USA
 TEL +1 978 657-8750 FAX +1 978 658-0349 sales@janis.com
 Visit our website at www.janis.com.

Order High Vacuum Components Online

www.ancorp.com

A&N Corporation offers convenient online ordering of high and ultra high vacuum components including:

- Flanges and Fittings (ISO, CF, and ASA)
- Couplings
- View Ports
- Feedthroughs
- Valves
- Weldable/Roughing Components

Prefer a paper catalog?
 Just email your address to request@ancorp.com or call us at:
 1-800-352-6431



A&N CORPORATION
 High Vacuum Components Since 1965

